



C058150A2

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com



High Flux Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
125	35 \pm 8%	XXXXXX	58150A2	X	Khaki

Dimensions	Uncoated		Coated Limits			Packaging
	(mm)	(in)	(mm)	(in)		
OD (A)	3.94	0.155	4.57	0.180	max	Bulk Pack 5 vials/box Box Qty= 7500 pcs
ID (B)	2.24	0.088	1.73	0.068	min	
HT (C)	2.54	0.100	3.18	0.125	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100kHz, 100mT max (mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _a (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Est. Weight (g)
	80%	50%							
1000	46	81	1000	2.7	2.35	2.10	9.5	20	0.19

Winding Information					Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)		Curie Temp: 500°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor		Coating Temp (Continuous up to): 200°C
				OD	4.77	
				HT	3.78	Notes:
Completely Full Window				Max OD	4.97	
				Max HT	4.38	
0%	9.20	40%	10.1	Surface Area (mm ²)		
20%	9.63	45%	10.2	Unwound Core		91
25%	9.76	50%	10.3	40% Winding Factor		100
30%	9.85	60%	10.6			
35%	9.97	70%	10.9			

