




0055297A2

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com
 www.mag-inc.com



| MPP Permeability (μ) | A_L (nH/T ²) | Core Marking | | | Coating Color |
|----------------------------|----------------------------|--------------|-------------|------------------|---------------|
| | | Lot Number | Part Number | Inductance Grade | |
| 19 | 10 \pm 8% | XXXXXX | 55297A2 | N/A | Grey |

| Dimensions | Uncoated | | Coated Limits | | | Packaging |
|------------|----------|-------|---------------|-------|-----|--|
| | (mm) | (in) | (mm) | (in) | | |
| OD (A) | 9.65 | 0.380 | 10.29 | 0.405 | max | Bulk Pack 4 bags/box Box Qty= 8000 pcs |
| ID (B) | 4.78 | 0.188 | 4.27 | 0.168 | min | |
| HT (C) | 3.96 | 0.156 | 4.60 | 0.181 | max | |

| Electrical Characteristics | | | Physical Characteristics | | | | | | |
|---|------------------------|-----|---|-------------------------|---|---|---------------------------------|--|------------|
| Watt Loss @ 100kHz, 100mT max (mW/cm ³) | DC Bias min (oersteds) | | Voltage Breakdown wire to wire min (V _{AC}) | Break Strength min (kg) | Window Area W _a (mm ²) | Cross Section A _e (mm ²) | Path Length L _e (mm) | Volume V _e (mm ³) | Weight (g) |
| | 80% | 50% | | | | | | | |
| 1600 | 190 | 320 | 1250 | 14.0 | 14.3 | 9.42 | 21.8 | 205 | 1.42 |

| Winding Information | | | | | Temperature Rating | |
|-------------------------|------|----------------|------|---------------------------------|--------------------|-------------------|
| Winding Length Per Turn | | | | Wound Coil Dimensions (mm) | | Curie Temp: 460°C |
| Winding Factor | (mm) | Winding Factor | (mm) | 40% Winding Factor | OD | 10.9 |
| | | | | | HT | 6.40 |
| 0% | 15.2 | 40% | 17.5 | Completely Full Window | Max OD | 11.5 |
| 20% | 16.2 | 45% | 17.8 | | Max HT | 7.60 |
| 25% | 16.6 | 50% | 18.1 | Surface Area (mm ²) | | |
| 30% | 16.9 | 60% | 18.8 | Unwound Core | 350 | |
| 35% | 17.2 | 70% | 19.5 | 40% Winding Factor | 450 | |
| Notes: | | | | | | |

