




0070726A7

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com



Kool Mμ Ultra Permeability (μ)	A _L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
60	175 ± 8%	XXXXXX	70726A7	N/A	Black

Dimensions	Uncoated		Coated Limits			Packaging Cardboard cut-outs Box Qty= 70 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	50.55	1.990	51.51	2.028	max	
ID (B)	24.77	0.975	24.00	0.945	min	
HT (C)	20.83	0.820	21.59	0.850	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100kHz, 50 mT max (mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _a (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Est. Weight (g)
	80%	50%							
75	45	100	3000	95	452	262	113.5	29,700	192

Winding Information						Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 500°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	56.7	Coating Temp (Continuous up to): 200°C
					HT	29.4	
0%	70.7	40%	83.2	Completely Full Window	Max OD	56.7	Notes: WL max @ 100kHz/100mT = 250mW/cc
					Max HT	39.8	
20%	77.0	45%	85.0	Surface Area (mm ²)			
25%	78.5	50%	86.8				
30%	79.7	60%	90.5	Unwound Core		8,400	
35%	81.7	70%	94.9	40% Winding Factor		11,000	

Typical DC Bias Performance

