




0075121A7

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



XFLUX Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
60	35 $\pm$ 8%	XXXXXX	75121A7	N/A	Black

Dimensions	Uncoated		Coated Limits			Packaging Bulk Pack 4 bags/box Box Qty= 2000 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	16.59	0.653	17.27	0.680	max	
ID (B)	10.16	0.400	9.53	0.375	min	
HT (C)	6.35	0.250	7.11	0.280	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 50 kHz, 100mT max(mW/cm³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _A (mm²)	Cross Section A _e (mm²)	Path Length L _e (mm)	Volume V _e (mm³)	Weight (g)
720	80%	50%	1250	23.0	71.2	19.2	41.2	791	8.11
	60.0	135							

Winding Information						Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 500°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	18.8	Coating Temp (Continuous up to): 200°C
					HT	10.1	
	Completely Full Window	Max OD	23.7	Notes:			
		Max HT	15.2				
0%	22.0	40%	26.8		Surface Area (mm²)		
20%	24.4	45%	27.6				
25%	25.0	50%	28.3	Unwound Core			
30%	25.6	60%	29.7				
35%	26.2	70%	31.4	40% Winding Factor		1,300	

Typical DC Bias Performance

