




0078382A7S01

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



XFLUX Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
26	19 $\pm$ 8%	XXXXXX	78382A7S01	N/A	Brown

Dimensions	Uncoated		Coated Limits			Packaging Bulk Pack 4 bags/box Box Qty= 2000 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	17.27	0.680	18.03	0.710	max	
ID (B)	9.65	0.380	9.02	0.355	min	
HT (C)	6.35	0.250	7.11	0.280	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 50 kHz, 100mT max(mW/cm³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _A (mm²)	Cross Section A _e (mm²)	Path Length L _e (mm)	Volume V _e (mm³)	Weight (g)
1000	80%	50%	2000	28.0	63.8	23.2	41.4	960	7.4000
	230	420							

Winding Information						Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 700°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	19.6	Coating Temp (Continuous up to): 200°C
					HT	10.1	
	Completely Full Window	Max OD	24.9	Notes:			
		Max HT	16.3				
0%	23.2	40%	28.0	Surface Area (mm²)			
20%	25.6	45%	28.6				
25%	26.2	50%	29.3				
30%	26.6	60%	30.8	Unwound Core		990	
35%	27.4	70%	32.4	40% Winding Factor		1,400	

Typical DC Bias Performance

