




0078451A7

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com
 www.mag-inc.com



XFLUX Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
60	108 \pm 8%	XXXXXX	78451A7	N/A	0

Dimensions					Packaging
Uncoated		Coated Limits			
	(mm)	(in)	(mm)	(in)	
OD (A)	42.90	1.689	43.83	1.724	Cardboard cut-outs Box Qty = 120 Pcs
ID (B)	24.20	0.953	23.40	0.921	
HT (C)	16.26	0.640	17.26	0.675	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 50kHz, 100mT (max, mW/cm ³)	DC Bias min (Oersteds)		Voltage Breakdown wire-to-wire min (V _{AC})	Break Strength (min, kg)	Window Area, W _A (mm ²)	Cross Section, A _e (mm ²)	Path Length, L _e (mm)	Volume V _e (mm ³)	Weight (g)
	80%	50%							
725	80	150	2000	98.8	430	147.5	102	15100	104

Winding Information					Temperature Rating	
Winding Length per Turn			Wound Coil Dimensions (mm)		Curie Temp (°C):	700 °C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	48.4
0%	55.0	40%	67.1	Completely Full Window	HT	21.8
20%	61.1	45%	68.9		Max OD	50.5
25%	62.5	50%	70.8	Surface Area (mm ²)	Max HT	23.9
30%	63.8	60%	74.2		Unwound Core:	5800
35%	65.6	70%	78.5		40% Wound:	8400

