




0078586A7S01

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



XFLUX Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
60	38 $\pm$ 8%	XXXXXX	78586A7S01	N/A	Brown

Dimensions	Uncoated		Coated Limits			Packaging Cardboard cut-outs Box Qty= 300 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	34.29	1.350	35.18	1.385	max	
ID (B)	23.37	0.920	22.56	0.888	min	
HT (C)	8.89	0.350	9.78	0.385	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 50 kHz, 100mT max (mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _A (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Weight (g)
900	80%	50%	3000	54	399	46.4	89.5	4,150	29
	100	170							

Winding Information						Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 700°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	40.5	Coating Temp (Continuous up to): 200°C
					HT	16.8	
	Completely Full Window	Max OD	50.1	Notes:			
		Max HT	29.0				
					Surface Area (mm²)		
0%	32.2	40%	44.0				
20%	38.1	45%	45.6				
25%	39.6	50%	47.3				
30%	40.6	60%	50.8		Unwound Core		2,900
35%	42.5	70%	54.9		40% Winding Factor		5,500

Typical DC Bias Performance

