

DIMENSIONS



(mm)	Nominal:	Tol. min.:	Tol. max.:
A	42.15	-0.85	+ 0.85
B	21.1	-0.2	+ 0.2
C	9.0	-0.25	+ 0.25
D	14.9 Min.		
E	29.5 Min.		
F	11.95	-0.25	+ 0.25
L	5.94	-0.13	+ 0.13
M	8.9	-0.25	+ 0.25
Eff. Parameters			
Ae mm ²	Amin mm ²	le mm	Ve mm ³
107.0	106.0	98.4	10500

INDUCTANCE

AL value (nH)	Test conditions
3495 ± 25%	10 kHz, < 0.5 mT, 25 °C

MARKING

F EC

CORE LOSSES

P _i max	Test conditions
210 mW/cm ³ (2.2 W/set)	25 kHz, 200 mT, 100 °C

NOTE

Spec. modifications	Previous	Revised
2005-06-22	A=42.8±0.64 B=21.1±0.18 E=30.4 Min. F=11.9±0.25 M=9.54±25 Losses: General F material	A=42.15±0.85 B=21.1±0.2 E=29.5 Min. F=11.95±0.25 M=8.9±0.25 Losses: Detail as indicated