

Specification for:

0J41203EC

110 Delta Drive
Pittsburgh, PA 15238
Phone: 412/696-1333
Fax: 412/696-0333
Email: magnetics@spang.com

DIMENSIONS



(mm)	Nominal:	Tol. min.:	Tol. max.:
A	12.7	-0.25	+ 0.25
B	5.69	-0.18	+ 0.18
C	3.18	-0.13	+ 0.13
D	3.96 Min.		
E	9.19 Min.		
F	3.18	-0.08	+ 0.08
L	1.57 Nom.		
M	3.05 Min.		
Eff. Parameters			
Ae mm ²	Amin mm ²	le mm	Ve mm ³
10.1	10.1	27.8	281

INDUCTANCE

AL value (nH)	Test conditions
Nom: 1367 Min.: 1025	10 kHz, < 0.5 mT, 25 °C

MARKING

No marking

LOSS FACTOR

$\tan \delta/\mu$ ($\times 10^{-6}$)	Test conditions
< 15	100 kHz, < 0.25 mT, 25 °C

NOTE

Spec. modifications	Previous	Revised
2005-06-22	Loss factor: General J material	Loss factor: Detail as indicated