




Specification for:  
**0W40200TC**

110 Delta Drive  
 Pittsburgh, PA 15238  
 Phone: 412/696-1333  
 Fax: 412/696-0333  
 Email:magnetics@spang.com

**DIMENSIONS**



(mm)	Uncoated Nominal:	Min:	Max:
O.D. (A)	2.54	2.33	2.75
I.D. (B)	1.27	1.06	1.48
Ht. (C)	1.27	1.09	1.45

Eff. Parameters		
$A_e$ mm <sup>2</sup>	$l_e$ mm	$V_e$ mm <sup>3</sup>
0.77	5.53	4.29

**INDUCTANCE**

AL value (nH/T <sup>2</sup> )	Test conditions
1750 ± 30%	10 kHz, 0.5 mT (For N = 5, use 0.026 mA), 25°C

**ELECTRICAL LOSSES**

$\tan \delta / \mu_i$	Production lot limit Average	Test conditions	
$\leq 3.5 \cdot 10^{-6}$	$\leq 3 \cdot 10^{-6}$	10 kHz	0.5 mT, 25°C
$\leq 55 \cdot 10^{-6}$	$\leq 45 \cdot 10^{-6}$	100 kHz	

**COATING**

Uncoated
----------

**NOTE**

Spec. Modifications	Previous	Revised
2006.11.29	LF: General W Material	LF: Detail as indicated