



C055106A9

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com
 www.mag-inc.com



| MPP Permeability (μ) | A_L (nH/T ²) | Core Marking | | | Coating Color |
|----------------------------|----------------------------|--------------|-------------|------------------|---------------|
| | | Lot Number | Part Number | Inductance Grade | |
| 200 | 250 \pm 8% | XXXXXX | 55106A9 | X | Gray |

| Dimensions | Uncoated | | Coated Limits | | | Packaging |
|------------|----------|-------|---------------|-------|-----|---------------------------------------|
| | (mm) | (in) | (mm) | (in) | | |
| OD (A) | 57.15 | 2.250 | 58.42 | 2.300 | max | Cardboard cut-outs Box Qty= 90 pcs |
| ID (B) | 35.56 | 1.400 | 34.36 | 1.353 | min | |
| HT (C) | 13.96 | 0.550 | 15.28 | 0.602 | max | |

| Electrical Characteristics | | | Physical Characteristics | | | | | | |
|---|------------------------|------|---|-------------------------|---|---|---------------------------------|--|------------|
| Watt Loss @ 100 kHz, 100mT max(mW/cm ³) | DC Bias min (oersteds) | | Voltage Breakdown wire to wire min (V _{AC}) | Break Strength min (kg) | Window Area W _A (mm ²) | Cross Section A _e (mm ²) | Path Length L _e (mm) | Volume V _e (mm ³) | Weight (g) |
| | 80% | 50% | | | | | | | |
| 1050 | 15.0 | 28.0 | 8000 | 107.0 | 927 | 144 | 143 | 20,700 | 190 |

| Winding Information | | | | | Temperature Rating | |
|-------------------------|------|----------------|------|---------------------------------|--------------------|---|
| Winding Length Per Turn | | | | Wound Coil Dimensions (mm) | | Curie Temp: 460 °C |
| Winding Factor | (mm) | Winding Factor | (mm) | 40% Winding Factor | | Coating Temp (Continuous up to): 200 °C |
| | | | | OD | 63.5 | Notes: |
| | | | | HT | 25.9 | |
| | | | | Completely Full Window | | Max OD |
| 0% | 53.0 | 40% | 71.0 | Max HT | 44.4 | |
| 20% | 61.9 | 45% | 73.2 | Surface Area (mm ²) | | |
| 25% | 64.3 | 50% | 76.0 | Unwound Core | | |
| 30% | 65.8 | 60% | 81.3 | 7,700 | | |
| 35% | 68.7 | 70% | 87.1 | 40% Winding Factor | | |
| | | | | 13,000 | | |

Typical DC Bias Performance

