




CMC013010005H

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1) 800-245-3984
 HK Sales: (852) 3102-9337
 magnetics@spang.com
 www.mag-inc.com

Dimensions				
	Bare (mm)	tol +/-	Case (mm)	tol +/-
OD (ØA)	13.0	TYP	14.7	Max
ID (ØB)	9.5	TYP	7.6	Min
HT (C)	5.0	TYP	7.0	Max



L (µH)	Conditions		Turns
10.33 Min	10 kHz	2 mT	1

A _e (cm ²)	L _e (cm)	Weight (g)	Color
0.07	3.5	1.8g (Ref)	White

PBT 130 °C

Material	Nanocrystalline
Saturation Flux Density	1.25 Tesla
Initial permeability	80,000
Curie Temperature	560 °C
Continuous working Temperature	-40 °C to +130 °C