




CMC020012008H

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1) 800-245-3984
 HK Sales: (852) 3102-9337
 magnetics@spang.com
 www.mag-inc.com

Dimensions				
	Bare (mm)	tol +/-	Case (mm)	tol +/-
OD (A)	20.0	typ	22.6	0.40
ID (B)	12.0	typ	10.6	0.40
HT (C)	8.0	0.20	10.0	0.40



A_L ($\mu\text{H}/\text{T}^2$)	Conditions	
61.5 +/- 30%	10 kHz	1.0 Volt
13.1 Min	100 kHz	1.0 Volt

A_e (cm^2)	L_e (cm)	Weight (g)	Color	
0.269	5.02	9.7 (Ref)	Black	PBT Class B 130°C

Material	Nanocrystalline
Saturation Flux Density	1.25 Tesla
Initial permeability	80,000
Curie Temperature	560 °C
Continuous working Temperature	-40 °C to +120 °C

