




**CMC040025015H96**

110 Delta Drive  
 Pittsburgh, PA 15238  
 NAFTA Sales: (1) 800-245-3984  
 HK Sales: (852) 3102-9337  
 magnetics@spang.com  
 www.mag-inc.com

Dimensions				
	Bare (mm)	tol +/-	Case (mm)	tol +/-
OD	40.0	typ	44.2	0.50
ID	25.0	typ	21.6	0.50
HT	15.0	0.20	18.9	0.50



$A_L$ ( $\mu\text{H}/\text{T}^2$ )	Conditions	
76 -- 142	10 kHz	2 mT
24.8 min	100 kHz	2 mT

$A_e$ ( $\text{cm}^2$ )	$L_e$ (cm)	Weight (g)	Color
0.92	10.2	68.0 (Ref)	Black

FR530 Class F (155°C)

Material	Nanocrystalline
Saturation Flux Density	1.25 Tesla
Permeability	96,000
Curie Temperature	560 °C
Continuous working Temperature	-40 °C to +155 °C