




CMC105075030H

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1) 800-245-3984
 HK Sales: (852) 3102-9337
 magnetics@spang.com
 www.mag-inc.com


Dimensions				
	Bare (mm)	tol +/-	Case (mm)	tol +/-
OD (ØA)	105.0	typ	109.4	1.00
ID (ØB)	75.0	typ	70.6	1.00
HT (C)	30.0	typ	34.5	1.00



L (µH)	Conditions		Turns
129 +/- 30%	10 kHz	1.0 Volt	1
36 min	100 kHz	1.0 Volt	1

A _e (cm ²)	L _e (cm)	Weight (g)	Color	
3.69	28.3	750 (Ref)	Black	PBT Class B 130°C

Material	Nanocrystalline
Saturation Flux Density	1.25 Tesla
Initial permeability	80,000
Curie Temperature	560 °C
Continuous working Temperature	-40 °C to +120 °C



11/8/2022