




CMF045030015H85

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1) 800-245-3984
 HK Sales: (852) 3102-9337
 magnetics@spang.com
 www.mag-inc.com

Dimensions				
	Bare (mm)	tol +/-	Case (mm)	tol +/-
OD (ØA)	45.0	TYP	48.2	0.50
ID (ØB)	30.0	TYP	27.6	0.50
HT (C)	15.0	TYP	17.9	0.50



L (µH)	Conditions		Turns
78 +/- 30%	10 kHz	2 mT	1
20 MIN	100 kHz	2 mT	1

A _e (cm ²)	L _e (cm)	Weight (g)	Color
0.92	11.8	78g (Ref)	Black

FR530 155 °C

Material	Nanocrystalline
Saturation Flux Density	1.25 Tesla
Initial permeability	80,000
Curie Temperature	560 °C
Continuous working Temperature	-40 °C to +155 °C