




CMF090060020H

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1) 800-245-3984
 HK Sales: (852) 3102-9337
 magnetics@spang.com
 www.mag-inc.com

Dimensions				
	Bare (mm)	tol +/-	Case (mm)	tol +/-
OD	90.0	typ	94.0	1.00
ID	60.0	typ	55.0	1.00
HT	20.0	typ	24.0	1.00



L (μH)	Conditions		Turns
61.0 -- 118	10 kHz	2 mT	1

A _e (cm ²)	L _e (cm)	Weight (g)	Color
2.5	23.50	425 (Ref)	Black

FR530 155 °C

Material	Nanocrystalline
Saturation Flux Density	1.25 Tesla
Initial permeability	80,000
Curie Temperature	560 °C
Continuous working Temperature	-40 °C to +155 °C