




EQG2619E026L088

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com
 www.mag-inc.com



| Edge Permeability (μ) | A_L (nH/T ²) | Core Marking | |
|-----------------------------|----------------------------|--------------|-----------------|
| | | Lot Number | Part Number |
| 26 | 95 ± 8% | XXXXXX | EQG2619E026L088 |

| | Dimensions | | Tolerance (±) | | Packaging |
|----------|------------|-------|---------------|-------|-----------------------|
| | (mm) | (in) | (mm) | (in) | |
| A | 26.50 | 1.043 | 0.30 | 0.012 | Est. Box Qty= 250 Pcs |
| B | 8.79 | 0.346 | 0.20 | 0.008 | |
| C | 19.00 | 0.748 | 0.20 | 0.008 | |
| D | 5.49 | 0.216 | 0.20 | 0.008 | Available Hardware |
| E | 22.60 | 0.889 | 0.20 | 0.008 | |
| F | 12.00 | 0.472 | 0.20 | 0.008 | |
| G | 15.00 | 0.590 | - | - | Min |

| Electrical Characteristics | | | Physical Characteristics | | | | | |
|--|------------------------|-----|--------------------------|--------------------------------------|--|------------------------|---------------------------------|-----------------------------|
| Watt Loss @ 100 kHz, 100mT max (mW/cm ³) | DC Bias min (oersteds) | | Break Strength typ (kg) | Window Area W_a (mm ²) | Cross Section A_e (mm ²) | Path Length L_e (mm) | Volume V_e (mm ³) | Est. Weight (Ea. Piece) (g) |
| | 80% | 50% | | | | | | |
| 550 | 210 | 325 | 34 | 58.2 | 120 | 49.5 | 5,834 | TBD |

Note: Standard AL is controlled with full window high turns test coils. Application coils with few turns often result in lower inductance than expected, or sometimes higher.

| Notes: | Temperature Rating |
|--------|--------------------|
| | Curie Temp: 500 °C |

