



EQK3222E026L152

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com
 www.mag-inc.com



| Kool M μ Permeability (μ) | A _L (nH/T ²) | Core Marking | |
|----------------------------------------|----------------------------------------|--------------|-----------------|
| | | Lot Number | Part number |
| 26 | 62 ± 8% | XXXXXX | EQK3222E026L152 |

| | Dimensions | | Tolerance (±) | | Packaging |
|---|------------|-------|---------------|-------|--------------------|
| | (mm) | (in) | (mm) | (in) | |
| A | 32.00 | 1.260 | 0.30 | 0.012 | Box qty: 240 pcs |
| B | 15.20 | 0.598 | 0.20 | 0.008 | |
| C | 22.00 | 0.866 | 0.30 | 0.012 | |
| D | 11.50 | 0.453 | 0.20 | 0.008 | Available Hardware |
| E | 27.60 | 1.087 | 0.30 | 0.012 | |
| F | 13.50 | 0.531 | 0.20 | 0.008 | |
| G | 20.43 | 0.804 | | Min | |

| Electrical Characteristics | | | Physical Characteristics | | | | | |
|----------------------------------------------------------------|-------------------------|-----|-------------------------------|-----------------------------------------------------|-------------------------------------------------------|---------------------------------------|---------------------------------------------|------------------------------|
| Watt Loss @ 100 kHz, 100mT Nominal (mW/cm ³) | DC Bias Nominal (Oe) | | Break Strength min (kg) | Window Area W _A (mm ²) | Cross Section A _e (mm ²) | Path Length L _e (mm) | Volume V _e (mm ³) | Weight (Ea. Piece) (g) |
| 650 | 80% | 50% | 24 | 81.08 | 152.3 | 79.9 | 12,168 | 31.7 |
| | 135 | 280 | | | | | | |

| | |
|--------|--------------------|
| Notes: | Temperature Rating |
| | Curie Temp: 500°C |

