


DIMENSIONS



(mm)	Nominal:	Tol. min.:	Tol. max.:
A	64.01	-1.27	+ 1.27
B	5.08	-0.13	+ 0.13
C	50.8	-1.02	+ 1.02
Eff. Parameters (with F_46410EC)			
Ae mm²	Amin mm²	le mm	Ve mm³
511.0	511.0	69.6	35539

INDUCTANCE

MARKING

AL value (nH/T²)	Test conditions (with FF46410EC)	FF46410IC PXXXXX
19699 ± 25%	10 kHz, < 0.5 mT, 25 °C	

NOTE

Spec. modifications	Previous	Revised
2005-06-22	Al=22594±25% A=64.0±0.76 C=50.8±0.81 Losses: General F material	Al=19609±25% A=64.01±1.27 C=50.8±1.02 Losses: Detail as indicated