




Specification for:  
**ZF42508TC**

110 Delta Drive  
 Pittsburgh, PA 15238  
 Phone: 412/696-1333  
 Fax: 412/696-0333  
 Email: magnetics@spang.com

**DIMENSIONS**



(mm)	Uncoated Nominal:	Coated Min:	Coated Max:
O.D. (A)	25.34	24.89	26.29
I.D. (B)	15.45	14.6	15.8
Ht. (C)	9.8	9.75	10.65

Eff. Parameters		
A <sub>e</sub> mm <sup>2</sup>	l <sub>e</sub> mm	V <sub>e</sub> mm <sup>3</sup>
48	61.5	2921

**INDUCTANCE**

AL value (nH/T <sup>2</sup> )	Test conditions
2900 ± 20%	10 kHz, 0.5 mT (For N = 5, use 0.96 mA), 25°C

**CORE LOSSES**

P <sub>L</sub> max	Production lot limit Max avg	Test conditions
643 (220 mW/cm <sup>3</sup> )	584 mW (200 mW/cm <sup>3</sup> )	25 kHz, 200 mT, 100°C

**COATING**

Epoxy rated for 200°C continuous operation.
Voltage breakdown rating 2000 V <sub>DC</sub> Min Wire-to-Wire.

**NOTE**

Spec. Modifications	Previous	Revised
2007.05.17	Bare Nom Ht = 10  Breakdown voltage > 1,000 V Losses: General F Material	Bare Nom Ht = 9.8  Breakdown voltage > 2,000 V <sub>DC</sub> Losses: Detail as indicated