




Specification for:
ZJ41306TC

110 Delta Drive
Pittsburgh, PA 15238
Phone: 412/696-1333
Fax: 412/696-0333
Email:magnetics@spang.com

DIMENSIONS



(mm)	Uncoated Nominal:	Coated Min:	Coated Max:
O.D. (A)	12.7	12.56	13.34
I.D. (B)	8.14	7.29	8.49
Ht. (C)	6.35	6.29	6.91

Eff. Parameters		
A _e mm ²	l _e mm	V _e mm ³
14.2	31.7	451.2

INDUCTANCE

A _L value (nH/T ²)	Test conditions	
2968 ± 20%	10 kHz	0.5 mT (For N = 1 use 1.49 mA), 25°C
≥ 0.9 x A _L @ 10 kHz	200 kHz	

ELECTRICAL LOSSES

tan δ / μ _i	Test conditions
≤ 12·10 ⁻⁶	100 kHz, 0.5 mT, 25°C

COATING

Epoxy rated for 200°C continuous operation.
Voltage breakdown rating 1,500 V _{DC} Min Wire-to-Wire

NOTE

Spec. Modifications	Previous	Revised
2006.10.31	Nom ID = 7.92 LF: General J Material	Nom ID = 8.14 LF: Detail as indicated