




Specification for:
ZJ42508TC

110 Delta Drive
 Pittsburgh, PA 15238
 Phone: 412/696-1333
 Fax: 412/696-0333
 Email:magnetics@spang.com

DIMENSIONS



(mm)	Uncoated Nominal:	Coated Min:	Coated Max:
O.D. (A)	25.34	24.89	26.29
I.D. (B)	15.45	14.6	15.8
Ht. (C)	10	10.15	10.65

Eff. Parameters		
A _e mm ²	l _e mm	V _e mm ³
48	61.5	2981

INDUCTANCE

A _L value (nH/T ²)	Test conditions	
4830 ± 20%	10 kHz	0.5 mT (For N = 1, use 2.96 mA), 25°C
≥ 0.9 x A _L @ 10 kHz	200 kHz	

ELECTRICAL LOSSES

tan δ / μ _i	Test conditions
≤ 12 · 10 ⁻⁶	100 kHz, 0.5 mT, 25°C

COATING

Epoxy rated for 200°C continuous operation.
 Voltage breakdown rating 2,000 V_{DC} Min Wire-to-Wire.

NOTE

Spec. Modifications	Previous	Revised
2006.12.15	Nom OD = 25.4 Nom ID = 15.5 LF: General J Material Breakdown voltage > 1,000 V A _L value up to 200 kHz	Nom OD = 25.34 Nom ID = 15.45 LF: Detail as indicated Breakdown voltage > 2,000 V _{DC} A _L at 200 kHz ≥ 0.9 x A _L at 10 kHz