




Specification for:
ZP44916TC

110 Delta Drive
Pittsburgh, PA 15238
Phone: 412/696-1333
Fax: 412/696-0333
Email:magnetics@spang.com

DIMENSIONS



(mm)	Uncoated Nominal:	Coated Min:	Coated Max:
O.D. (A)	49.1	48.48	50.22
I.D. (B)	33.8	32.69	34.41
Ht. (C)	15.6	15.64	16.64

Eff. Parameters		
A _e mm ²	l _e mm	V _e mm ³
118	127	15010

INDUCTANCE

AL value (nH/T ²)	Test conditions
2950 ± 25%	10kHz, 0.5 mT (For N = 5, use 0.47 mA), 25°C

CORE LOSSES

P _L max	Production lot limit Max avg	Test conditions
1846 mW (123 mW/cm ³)	1681 mW (112 mW/cm ³)	100 kHz, 100 mT, 100°C
-	-	-

COATING

Epoxy rated for 200°C continuous operation.
Voltage breakdown rating 2000 V Min Wire-to-Wire.

NOTE

Spec. Modifications	Previous	Revised
2006.01.12	Bare Nom Ht = 15.9 Losses: General P Material Breakdown voltage > 1,000 V	Bare Nom Ht = 15.6 Losses: Detail as indicated Breakdown voltage > 2,000 V